



# STEP-OPENING ENTERPRISE CO.,LTD

## DONGGUAN YUZHAN CHEMICAL CO.,LTD

TAIWAN HEADQUARTERS :

NO.349-1 GANGSHAN RD., GANGSHAN DIST., KAOHSIUNG CITY., TAIWAN

TEL:886-7-6220803 FAX:886-7-6220805

DONGGUAN YUZHAN :

JINFENGHUANG INDUSTRIAL ZONE, FENGANG TOWN, DONGGUAN CITY,  
GUANGDONG PROVINCE, CHINA

TEL:86-769-87550418(代表号) FAX:86-769-87550438

### UT-486A “Alcohol Resistance” Top Coat

#### 【Instruction】

UT-486A “Alcohol Resistance” Top Coat is designed to Vacuum Metallization manufacturers. It is also used as a middle coating, mix with dyestuffs, between aluminum layer and top coat of UV coatings. Excellent performance on adhesion, gloss, fullness, abrasion resistance, alcohol resistance. It can be used on parts of products such as cosmetics, perfume caps and plated products.

#### 【Application】

UT-486A “Alcohol Resistance” Top Coat can spray directly or add into dyestuffs for spraying based on needs and quality of materials. The spraying pressure should be 3.0-3.5kg/cm<sup>2</sup> and the distance should be 15-20 cm.

UT-486A “Alcohol Resistance” Top Coat is air dry top coat. Because of its alcohol resistance, baking condition should be 60-70°C and 20-30 minutes if want to accelerate reactions.

#### 【Base Coat】

Please use UB-269 Series, UP-916, UB-2485B, UB-256B.

#### 【Notices】

1. Please use Ketone solvents to mix with oil dyestuffs. DO NOT USE DYESTUFFS CONTAINS ALCOHOL SOLVENTS.
2. Please clean up the sprayer and the tube with Ketone solvents before and after spraying to avoid incompatibilities occur if using same equipment with other top coats.
3. Please leave the coating 24 hours after spraying, it would have more accurate result of alcohol test because solvents might not evaporate completely.
4. If the coating is too thin, it would have rainbow situation easily ; please thicken the top coating by spraying on it.
5. Due to special ingredients of this product, too much lacquer dusts accumulated may cause burning. They must be applied with water-based coating equipment and clean the sprayer and relevant devices with water frequently. Store the lacquer dusts in outdoor within water in case the burning
6. Please keep good air circulation in working place to avoid harming health due to long-term breathing in solvent. If chemicals splash into eye or on skin accidentally, immediately flush contacting area by huge amount of water then send to medical

treatment.

7. UT-486A "Alcohol Resistance" Top Coat must be stored in cool and dry indoor room under 40°C. The expired time is one year in unopened situation.
8. Please keep cap closing after opening and finish within one week to avoid affecting quality because of solvent evaporation.