



STEP-OPENING ENTERPRISE CO., LTD

DONGGUAN YUZHAN CHEMICAL CO., LTD

TAIWAN HEADQUARTERS:

NO.349-1 GANGSHAN RD., GANGSHAN DIST., KAOHSIUNG CITY., TAIWAN

TEL:886-7-6220803 FAX:886-7-6220805

DONGGUAN YUZHAN:

JINFENGHUANG INDUSTRIAL ZONE, FENGANG TOWN, DONGGUAN CITY,
GUANGDONG PROVINCE, CHINA

TEL:86-769-87550418(代表号) FAX:86-769-87550438

UVB-725 “Heat Resistance” UV Base Coat

【Instruction】

UVB-725 “Heat Resistance” UV Base Coat is made to Vacuum Metallization manufacturers for UV Curing Base Coat. Excellent performance on heat resistance, adhesion, gloss. Applicable to heat resistance PC materials. It can be used on parts of products such as cosmetics, digital products, appliance, decoration, LED holder.

【Application】

UVB-725 “Heat Resistance” UV Base Coat can spray on materials directly then leveling evenly after IR. IR condition is 60-70°C in 3-6 mins or baking before UV process. Suggest using encompass or straight type UV curing machine with UV energy 800-1000mj/cm² after baking.

【Notices】

1. UVB-725 “Heat Resistance” UV Base Coat is a UV curing product which reacts with UV easily. It must be stored in a cool and dry indoor place without sunshine to keep its stable.
2. Plastic materials usually contaminate with internal lubricant, mold release agent, and dust during injection process. To ensure good adhesion and smooth surface during Vacuum Metallization, please clean the materials with solvent before coating process.
3. The procedure of Infrared radiation (IR) Temperature, Time, and UV energy must fulfill the requirements to ensure quality of coating products. UV energy will decrease by UV lamp aging and voltage supply. Please replace with new UV lamp and stable voltage to ensure coatings dry.
4. Please keep good air circulation in working place to avoid harming health due to long-term breathing in solvent. If chemicals splash into eye or on skin accidentally, immediately flush contacting area by huge amount of water then send to medical treatment.
5. UVB-725 “Heat Resistance” UV Base Coat must be stored in cool and dry indoor room under 40°C. The expired time is one year in unopened situation.
6. Please keep cap closing after opening and finish within one week to avoid affecting quality because of solvent evaporation.