



STEP-OPENING ENTERPRISE CO.,LTD DONGGUAN YUZHAN CHEMICAL CO.,LTD

TAIWAN HEADQUARTERS:

NO.349-1 GANGSHAN RD., GANGSHAN DIST., KAOHSIUNG CITY., TAIWAN

TEL:886-7-6220803 FAX:886-7-6220805

DONGGUAN YUZHAN:

JINFENGHUANG INDUSTRIAL ZONE, FENGANG TOWN, DONGGUAN CITY,
GUANGDONG PROVINCE, CHINA

TEL:86-769-87550418(代表号) FAX:86-769-87550438

S-28 Abrasion Resistance Agent

【Instruction】

S-28 Abrasion Resistance Agent is made to improve abrasion resistance of top coats for Vacuum Metallization. Applicable to top coats such as UT-801, UT-117, UT-811, UT-842, UT-563(as top coat).

【Application】

Add to top coat then stirring evenly. The percentage of S-28 Abrasion Resistance Agent is 0.1-0.2% of all coatings. The ratio can be adjusted base on requirement.

【Notices】

1. **S-28 Abrasion Resistance Agent could affect rework ability of products. USE CAREFULLY.**
2. **Need to notice mix condition when add S-28 Abrasion Resistance Agent. Please stop adding S-28 Abrasion Resistance Agent immediately if the mixture becomes cloudy.**
3. Please keep good air circulation in working place to avoid harming health due to long-term breathing in solvent. If chemicals splash into eye or on skin accidently, immediately flush contacting area by huge amount of water then send to medical treatment.
4. S-28 Abrasion Resistance Agent must be stored in cool and dry indoor room under 40°C. The expired time is one year in unopened situation.
5. Please keep cap closing after opening and finish within one week to avoid affecting quality because of solvent evaporation.